

瞬间胶 VA 250 Black



适用于特殊要求

高粘度，慢速固化，橡胶填充，耐高温

由于该款产品具残余弹性，它特别适用于气候多变的环境中，不受长期湿度的影响。

VA250Black适用于各种橡胶和塑料材质，如硬质橡胶或泡沫橡胶，以及金属/塑料的粘接。它可投入应用于不同的工业领域。

技术参数

酯型	乙烷基
质地	黑色
依据 Brookfield 在温度+20°C时的粘度	2.000 - 3.000 mPa·s
最大粘接缝隙	0,2 mm
达到初始粘附力（粘接铝）	90 -120 秒
达到初始粘附力（粘接NBR橡胶）	20 -40 秒
达到初始粘附力（粘接硬质PVC）	40 -80 秒
达到最终强度	24 h
依据 DIN EN 1465，拉伸剪切强度为：	
钢质表面 喷砂处理	24 N/mm ²
铝，喷砂处理	18 N/mm ²
硬质PVC	13 N/mm ²
ABS	12 N/mm ²
PC	13 N/mm ²
NBR	> 8 N/mm ²
耐温性	-55至+140，软化温度+160 °C
ISSA 编码	75.629.08/09/20/21
IMPA 编码	815257/58/59/60

表面预处理

为确保粘接效果，待粘接的物体表面需干燥、清洁（可使用WEICON表面清洁剂进行清洁与去脂）。光滑表面需做粗糙处理。

难以粘接的塑料表面（如PE、PP、POM、PTFE）、热塑性弹性体（TPE）以及硅酮，可使用WEICON瞬间胶底漆进行预处理。

操作

- WEICON 瞬间胶使用时仅需单侧涂胶。

- 粘结厚度应在0.05 mm至0.2mm之间，否则无法完全固化。

- 若需粘接较大的平面，则需要逐滴滴加WEICON瞬间胶，以避免产生内部张力。

- WEICON瞬间胶非常经济实惠，一滴胶水能粘接约3 – 5cm²的面积。

- 粘接操作应在相对湿度40 – 80%环境中进行。当相对湿度低于40%时，固化速度会大大减慢，甚至无法固化。当空气湿度高于80%时，则会出现瞬间固化的现象。在这种情况下，一些材料的粘接强度会下降10 – 15%，这是由粘接层的内部张力所致。

- 当待粘接的物体表面碱性（pH值大于7）时，胶水的固化速度会加快；反之，酸性表面则会减慢固化速度。在极端环境下，聚合反应有可能被完全抑制。

储藏

WEICON氰基丙烯酸盐粘合剂需储存在干燥、阴凉处。在室温（18 – 25°C）环境下，保质期为至少9个月。在5°C（如冰箱、冰柜）环境下，保质期可延长至12个月。

安全与健康

使用WEICON产品时，需注意产品的物理性、安全性、毒理性、生态性的详细参数以及我们EG材料安全数据表（www.weicon.com）的具体信息。

包装

12600012-47	瞬间胶 VA 250 Black 12 g
12600030-47	瞬间胶 VA 250 Black 30 g
12600060-47	瞬间胶 VA 250 Black 60 g
12600500	瞬间胶 VA 250 Black 500 g

产品配件

12450010	用于聚烯烃的瞬间胶底漆，
12500150	瞬间胶催化剂喷射剂, 150 ml
12505150	瞬间胶催化剂AC,
12955170	精密胶嘴，
12955175	精密胶嘴，

提示
本资料中列出的所有产品，其参数和建议是在实验室的测试结果及经验总结，不得被视为对产品特性的保证。由于每一个用的实际应用情况并不在我们的认知、控制及责任范围内，我们对这些信息并不承担任何义务。我们保证我们的产品符合并遵守我们销售条款中承诺的高品质、无瑕疵的要求。我们建议用户通过自行试验来论证其希望选用的产品是否完全符合预期。因用户未遵照指定的操作方法使用产品而造成损失的情况，用户将独自承担全部责任。

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322
0
info@weicon.de
www.weicon.de

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709
0088
info@weicon.co.za
www.weicon.co.za

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae
www.weicon.ae

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg
www.weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Czech Republic
s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Kimya Sanayi Tic. Ltd.
Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730
763
office@weicon.com
www.weicon.com.ro

WEICON Italia S.r.l.
Italy
phone (+39) 0102924871
info@weicon.it
www.weicon.it

Contact VA 250 Black Cyanoacrylate Adhesive



Cyanoacrylate Adhesive for special requirements rubber-filled, high viscosity high temperature resistant

VA 250 Black is highly viscous (2000-3000 mPa•s) and temperature resistant between -50°C (-58°F) and +140°C (+284°F). It hardens slowly and with residual elasticity, is rubber-filled and black, and has high peel and impact strength.

Thanks to its curing with residual elasticity, WEICON Contact VA 250 Black is particularly suitable under changing climatic conditions. It is insensitive even under a longer influence of humidity. It is best suited for the bonding of diverse rubber materials such as solid rubber or cellular rubber, plastics and metal/plastic joints.

WEICON Contact VA 250 Black can be used in various fields of industry.

Technical Data

Ester type	Ethyl
Texture	black
Viscosity at +20°C (+68°F) according to Brookfield	2.000 - 3.000 mPa•s
Max. Gap Bridging	0,2 mm
Initial strength on aluminium	90 -120 sec.
Initial strength on NBR-Rubber	20 -40 sec.
Initial strength on hard PVC	40 -80 sec.
Final strength approx. after	24 h
Shear strength according to DIN EN 1465 at:	
Steel sand blasted	24 N/mm²
Sand-blasted Aluminium	18 N/mm²
Rigid PVC	13 N/mm²
ABS	12 N/mm²
PC	13 N/mm²
NBR	> 8 N/mm²

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Temperature resistance	-55 to +140 / squatting temp. +160 °C
ISSA-Code	75.629.08/09/20/21
IMPA-Code	815257/58/59/60

Surface pre-treatment

To ensure a perfect bonding, the surfaces to be joined must be clean and dry (to clean and degrease use WEICON Surface Cleaner). Smooth surfaces should be mechanically roughened. To improve the adhesion on difficult to bond plastics (e.g. PE, PP, POM, PTFE), thermoplastic elastomers (TPE) and Silicone, WEICON CA-Primer can be applied on the surface.

Processing

- Apply WEICON Contact Cyanoacrylate Adhesive only on one of the surfaces to be bonded. The bond line should be between 0.05 mm and max. 0.2 mm (acc. to type) in thickness. Otherwise complete hardening cannot be guaranteed.

- For bonding large surfaces WEICON Contact Cyanoacrylate Adhesive should be applied drop by drop to avoid inner tensions.

- WEICON Contact Cyanoacrylate Adhesives are very economical. One drop is sufficient to cover approx. 3 - 5 cm² of bonded surface.

- The parts to be joined should be bonded in an atmosphere of 40 - 80 % relative humidity. In conditions of below 40%, the cure will be considerably slowed or even inhibited. With a relative air humidity of more than 80% or with basic substrates (e.g. glass), shock-curing can occur. In such cases, some materials show a drop in bond strength of 10 - 15 %, due to inner tensions in the bond line.

- Basic-reacting surfaces (pH-value smaller 7) will speed up the cure whereas acidic-reacting surfaces will retard and, under extreme conditions, completely inhibit the polymerization.

Storage

WEICON Contact Cyanoacrylate Adhesives can be stored in the unopened original container for at least 9 months at room temperature (+ 18°C to + 25°C). Keep away from moisture and direct sunlight. At temperatures of about + 5°C, the shelf life can be extended up to 12 months.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de
www.weicon.de

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za
www.weicon.co.za

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae
www.weicon.ae

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg
www.weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com
www.weicon.com.ro

WEICON Italia S.r.l.
Italy
phone (+39) 0102924871
info@weicon.it
www.weicon.it

Technical Datasheet

Create Date:17.08.2020 - Seite2/2

Available sizes:

12600012	Contact VA 250 Black Cyanoacrylate Adhesive 12 g
12600020	Contact VA 250 Black Cyanoacrylate Adhesive 20 g
12600030	Contact VA 250 Black Cyanoacrylate Adhesive 30 g
12600060	Contact VA 250 Black Cyanoacrylate Adhesive 60 g
12600500	Contact VA 250 Black Cyanoacrylate Adhesive 500 g

Accessories:

12450010	CA-Primer for Polyolefines,
12500150	CA-Activator Spray, 150 ml
12505150	CA-Activator Spray AC, 150 ml
12955170	Dosing Tips,
12955175	Dosing Tips,

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de
www.weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae
www.weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com
www.weicon.com.ro

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za
www.weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg
www.weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Italia S.r.l.
Italy
phone (+39) 0102924871
info@weicon.it
www.weicon.it